

CEE-BEE STRIPPER A-292

by Cee-Bee®



d a t a s h e e t

CEE-BEE STRIPPER A-292 is a viscous paint stripper that rapidly and effectively strips a wide variety of coatings.

BENEFITS

- Strips alkyd and modified alkyd enamels, nitrocellulose and acrylic lacquers, most moisture cured polyurethanes and many air-dried epoxies.
- Readily removes carbon deposits from bare metal surfaces.
- Effectively strips coatings from fiberglass radomes.
- Viscous. Clings to incline, vertical and overhead surfaces.
- Safe on all common aircraft structural metals, including aluminum, cadmium plated steel, mild steel, magnesium and high strength steel.
- Non-flammable. Low toxicity.
- Contains no phenolics or cyanides. Surfactants biodegradable.

CONFORMS TO

- **DOUGLAS 13-1**
- **BOEING 737 AND 747 MANUALS**
- **BOEING D6-17487, REVISION P**
- **T.O.1-1-8**
- **MIL-R-81294D, TYPE II, CLASS 2 (QPL)**
- **FEDERAL EXPRESS**
- **ROLLS ROYCE OMAT NO. 154B**
- **LOCKHEED EPS 32-2350**
- **TT-R-248B**

**NOTE: To place an order, call or FAX Customer Service at
800-932-7006 / FAX 1-216-441-1377
Cee-Bee Stripper A-292 Product Code #23007**



NOTES PRIOR TO HANDLING

Before using your McGean-Rohco, Inc. products, all safety and operating instructions should be read and understood. If you have any questions, please contact your McGean-Rohco representative before proceeding.

USE PROCEDURES

Paint Stripping

1. Surface should be dry and below 110°F (43°C).
2. Apply a very thin, uniform film of stripper with brush, roller or non-atomizing spray.
3. When the coating begins to absorb the stripper, apply another uniform film.
4. Allow the stripper to dwell until the coating is loosened from the substrate,
5. Agitate with a stiff bristle brush and reapply the stripper to areas not completely released.
6. When stripping action is complete, squeegee or scrape off loosened coating and excess stripper and collect for disposal.
7. Rinse with high-pressure water to remove paint and stripper residues.

Carbon Removal from Unpainted Metals

1. Surface should be dry and below 110°F (43°C)
2. Apply a very thin, uniform film of stripper with brush, roller or non-atomizing spray.
3. When the coating begins to absorb the stripper, apply another uniform film.
4. Allow the stripper to dwell until the coating is loosened from the substrate.
5. Agitate with a stiff bristle brush.
6. Rinse with flowing water. Do not allow stripper or rinse water to contact any adjacent painted area.

PROPERTIES

- A thick, hazy yellow liquid with a pungent odor.
- No flash point. pH 12.

PRECAUTIONS

- Contains chlorinated hydrocarbons and ammonia. Use with good ventilation. Do not use in confined spaces.
- Avoid contact with eyes and skin. Wear gloves and goggles or face shield. Use full rack gear for large-scale operation.
- In case of accidental contact with eyes or skin, flood area with water. Seek medical attention if irritation persists.
- May damage acrylic plastic and electrical wiring insulation.

Copyright 1990 McGean-Rohco, Inc.

Rev. 7/12