

CEE-BEE STRIPPER A-458

by Cee-Bee®



d a t a s h e e t

CEE-BEE STRIPPER A-458 is a specifically designed for removing polysulfide basecoat paint systems. Also used for stripping polysulfide sealants and similar sealing compounds.

BENEFITS

- Provides excellent removal of polyurethane and other paint systems with polysulfide basecoats.
- Very effectively removes polysulfide sealants and similar sealants as well as natural rubber base sealants and coatings.
- Thixotropic. Clings to vertical, inclined and overhead surfaces.
- Contains evaporation retardant to minimize solvent loss.
- Free rinsing.
- Safe on aircraft structural metals, including high strength steel, mild steel, stainless steel, cadmium plated steel, aluminum and magnesium.
- Contains no phenol, heavy metals or mercaptans.
- Surfactants biodegradable.

CONFORMS TO

- **MIL-R-81294C, TYPE III, CLASS 2**
- **T.O.1-1-8, SECT. II**

**NOTE: To place an order, call or FAX Customer Service at
800-932-7006 / FAX 1-216-441-1377
Cee-Bee Stripper A-458 Product Code # 23055**



NOTES PRIOR TO HANDLING

Before using your McGean-Rohco, Inc. products, all safety and operating instructions should be read and understood. If you have any questions, please contact your McGean-Rohco representative before proceeding.

USE PROCEDURES

Coating removal

1. The surface must be thoroughly clean, free from water and at a temperature below 100 °F (38°C). 60 to 90°F (16-32°C) is desirable.
2. Flow on or apply Cee-Bee A-458 by brush or non-atomizing spray. Allow stripper to dwell until coating is penetrated and swells. Apply additional Cee-Bee A-458 if required to keep the surface wet with stripper.
3. When the coating is completely lifted from the substrate, thoroughly agitate with a stiff bristle brush. Apply more stripper to areas still adhering to the surface.
4. When stripping action is complete, thoroughly rinse surface with a high pressure water spray.

Sealant Removal

1. The surface must be thoroughly clean, free from water and at a temperature below 100 °F (38°C) is desirable.
2. Apply Cee-Bee A-458 with a brush. Allow stripper to dwell until sealant is penetrated and dissolved. Apply additional stripper if required to keep surface wet.
3. When sealant is completely lifted from substrate, remove with scraper which will not scratch surface. Reapply stripper to any spots of sealant which are not readily removed with a scraper.
4. When removal is complete, flush surface with a spray rinse of water or wipe clean with cloths wet with water.

PROPERTIES

- Thick, light colored liquid. No flash point up to and including initial boiling point.

PRECAUTIONS

- Contains methylene chloride.
- Do not use in confined spaces. Adequate ventilation must be provided. Avoid breathing vapors.
- Avoid all eye and skin contact. Use face shield, apron, gloves and boots.
- In case of accidental contact with eyes or skin, flood with water immediately. Seek medical attention if irritation persists.
- Open containers slowly to avoid spewing of contents.
- Do not contaminate bath with water. Water contamination will adversely effect stripping performance.

Copyright 1990 McGean-Rohco, Inc.

Rev. 2/01